



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 711 506 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
23.04.2003 Bulletin 2003/17

(51) Int Cl.7: **A23G 3/30**

(21) Application number: **95202759.7**

(22) Date of filing: **13.10.1995**

(54) **POLYESTER OR POLYCARBONATES AS GUM BASE FOR CHEWING GUM**

POLYESTER ODER POLYCARBONATE ALS KAUMASSE FÜR KAUGUMMI

POLYESTERS ET POLYCARBONATES EN TANT QUE MASSE A MACHER DANS LES GOMMES
A MACHER

(84) Designated Contracting States:
BE DE FR GB IT NL SE

(30) Priority: **14.10.1994 NL 9401703**

(43) Date of publication of application:
15.05.1996 Bulletin 1996/20

(73) Proprietor: **Hycail B.V.**
9804 TG Noordhorn (NL)

(72) Inventors:
• **Grijpma, Dirk Wybe**
NL-9712 CP Groningen (NL)
• **Laimböck, Johannes Franciscus**
NL-9712 CP Groningen (NL)

• **Pennings, Albert Johan**
NL-9712 CP Groningen (NL)

(74) Representative:
Smulders, Theodorus A.H.J., Ir. et al
Vereenigde
Postbus 87930
2508 DH Den Haag (NL)

(56) References cited:
EP-A- 0 258 780 **WO-A-92/15285**
WO-A-95/09601 **FR-A- 2 572 282**
FR-A- 2 635 685 **GB-A- 2 166 651**
US-A- 3 800 006 **US-A- 5 196 200**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The invention relates to a chewing gum formulation which has improved properties with regard to degradability.

[0002] It is known that chewing gum can give rise to a certain extent of environmental pollution inasmuch as it is very difficult to remove, if it can be removed at all, after use. It has already been proposed to replace a number of components of the chewing gum by components that are either taken up by the user during chewing or have a less poor biodegradability than the components conventionally used. EP-A 566,174, for example, discloses the use of a conventional elastomer in combination with a wholly or partly hardened oil. It is true that in the use of this formulation the poorly degradable paraffin can be replaced by another component, but the problems involved in the use of conventional, often synthetic elastomers remain.

[0003] The present invention is based on the surprising insight that it is possible to replace the conventional, non-degradable elastomers that are used in the gum base of chewing gum by biodegradable polymers. In combination with other biodegradable additives, a chewing gum is thus obtained whose organic components are biodegradable after use.

[0004] The invention relates to a biodegradable, i.e. degradable in the environment, chewing gum comprising one or more conventional chewing gum components and, included in the gum base, at least one polymer selected from the group of polyesters and polycarbonates having a glass transition temperature of 37°C at a maximum, which polymer contains chemically unstable compounds in the polymer chain.

[0005] Such chemically unstable compounds are broken down under the influence of light or hydrolytically into components that are preferably water-soluble and non-toxic.

[0006] According to the invention, the biodegradable chewing gum comprises one or more conventional chewing gum components and as gum base at least one polyester having a glass transition temperature of 37°C at a maximum. Such a polyester is more particularly based on the polymerisation product of one or more cyclic esters, such as lactide, glycolide, trimethylene carbonate, δ -valerolactone, β -propiolactone and ϵ -caprolactone. Such polyesters can for instance be used in the form of block copolymers or as mixtures of two or more homo- and/or copolymers.

[0007] It is preferred to use a gum base which is based on a copolymer or a block or graft copolymer of a lactide and one or more other cyclic esters, such as glycolide, trimethylene carbonate, δ -valerolactone, β -propiolactone and ϵ -caprolactone, or a mixture of two or more polymers, with at least one of the polymers containing lactide. In this preferred embodiment, it is preferred to use systems which contain at least 50% by weight of lactide units, more particularly at least 80%, based on

the total of the polymers.

[0008] The preparation of such polymers for use as gum base can be effected in conventional manner, for instance by ring-opening polymerisation in the presence of suitable catalysts. These catalysts can be based on compounds of transition metals, which are preferred to have the GRAS status (generally recognised as safe).

[0009] Surprisingly, it has been found that with such biodegradable polymers a chewing gum can be obtained which has a structure and chewing characteristics comparable to those of chewing gum based on conventional, non-degradable elastomers. It has moreover been found that the adhesion of such a chewing gum to other materials, and more particularly to stone and smooth surfaces, is comparatively slight. This means that such a chewing gum can be removed from stones with much less effort.

[0010] Optionally, the chewing gum according to the invention contains, in addition to the biodegradable elastomer component already described, one or more other biodegradable gum base components, together forming a water-insoluble, chewable gum base. Further, the chewing gum generally contains a water-soluble part and a water-insoluble flavour component. These last two components are generally taken up in the mouth during chewing, with the water-insoluble flavour component diffusing from the gum base along with the water-soluble component.

[0011] The suitable supplementary gum base components are, for instance, the components described in the above-mentioned European patent application 566,174, such as a fully hardened stearine fraction. The gum base can moreover contain yet other, biodegradable components, such as emulsifiers and gum base solvents. Suitable as emulsifiers are, for instance, lecithin and fatty acid monoglycerides, diglycerides and triglycerides.

[0012] The gum base may further include fillers, such as calcium carbonate, magnesium carbonate, talc, tricalcium phosphate, as well as mixtures thereof. The amount of filler is generally 10 to 15% of the gum base. If desired, the gum base can also contain antioxidants, which must naturally be food-approved. Suitable antioxidants include butylhydroxide anisol and butylhydroxide toluene. Suitable amounts of antioxidant are between 0.01 and 0.1% by weight, based on the gum base.

[0013] The water-soluble component of the chewing gum, which is preferably 5 to 95% of the chewing gum and more particularly 10 to 50% by weight, comprises, for instance, plasticizer, sweeteners and combinations thereof. The plasticizers, or softeners, are added to the chewing gum in order to improve the chewability and mouthfeel of the gum. Plasticizers or softeners generally account for 0.5 to 15% by weight of the chewing gum. Examples are glycerin, lecithin and combinations thereof. The water-soluble component also contains, for instance, sorbitol, hydrogenated starch hydrolysates, cane sugar syrup and combinations thereof, as well as

saccharide containing components conventionally used in chewing gum, *inter alia* sucrose, dextrose, maltose, dextrin, dried invert sugar, fructose, levulose, galactose, alone or in combination. Sugar-free sweeteners comprise components that contain sweetening characteristics but are free of the known sugars, and comprise, for instance, sugar alcohols, such as sorbitol, mannitol, xylitol, hydrogenated starch hydrolysates, maltitol, as well as the known sweeteners aspartame, sucrose, acesulfame and saccharide, either alone or in combination.

[0014] The chewing gum can further contain an amount of flavouring agent, which is preferably between 0.1% and 10% by weight of the chewing gum. Suitable flavouring agents are generally the known food approved flavours, such as oils of plants and fruits, such as citrus oil, fruit extracts, peppermint oil, clove oil, aniseed oil. It is also possible to add artificial flavour.

[0015] Additional ingredients, such as colouring agents and medicinal components, as well as mouth conditioners, can also be added to the chewing gum.

[0016] Generally, the chewing gum according to the invention is manufactured by successively adding the various chewing gum ingredients to a suitable mixer. After the ingredients have been thoroughly mixed, the mixture is discharged from the mixer and brought into the desired form, for instance by rolling and slicing, extruding or pelleting. In general, the ingredients are first mixed by melting the gum base which is added to a rotating mixer. The base can also be melted in the mixer itself. Colouring agents are preferably added at this time. A plasticizer is then brought into the mixer together with the sweetener and a part of the filler. The optional further required components can be added next. After mixing has been completed, the chewing gum is taken from the mixer and brought into the desired form.

[0017] The invention will now be elucidated in and by the following examples.

EXAMPLE 1

[0018] An amorphous, non-crystallizable copolymer of 80 mol.% L-lactide and 20 mol.% D-lactide was prepared by ring-opening polymerisation in the melt, in the presence of 0.1% by weight tin octoate as catalyst. To this polymer was added an amount of 20% by weight of ϵ -caprolactone, whereafter, under nitrogen and with continuous mechanical stirring, the mixture was heated to 150°C. To the homogeneous mixture, again 0.1% by weight tin octoate as catalyst was added, whereafter the polymerisation was completed.

[0019] The obtained polymer had a glass transition temperature (DSC, heating rate 10°C/min) of 15°. During chewing the polymeric material provided a chew feel strongly resembling that of conventional chewing gum. The degradation products of this copolymer are L-lactic acid, D-lactic acid and ω -hydroxyhexanoic acid, all non-toxic and water-soluble compounds.

[0020] On the basis of this polymer, a chewing gum

was prepared using conventional additions and methods.

EXAMPLE 2

[0021] On the basis of the copolymer of Example 1 as gum base, a number of types of chewing gum having the following compositions are prepared.

- 64% by weight sugars and sweeteners (sorbitol, xylitol and saccharine), 1% by weight aroma and 35% by weight gum base, and emulsifier.
- 40% by weight sugar, 2% by weight aroma and 58% by weight gum base, and emulsifier.
- 35% by weight sugar, 3% by weight aroma and 62% by weight gum base, and emulsifier.

EXAMPLE 3

[0022] An amorphous, non-crystallizable copolymer of 25 mol.% L-lactide, 25 mol.% D-lactide and 50 mol.% ϵ -caprolactone was prepared by ring-opening polymerisation in the melt, in the presence of 0.1% by weight tin octoate as catalyst.

[0023] The obtained polymer has a glass transition temperature (DSC, heating rate 10°C/min) of -10°C.

[0024] To the polymer formed, under nitrogen, 40% by weight of sorbitol and an effective amount of emulsifier were added and mechanically mixed. During chewing the polymeric material provided a chew feel strongly resembling that of a conventional chewing gum.

EXAMPLE 4

[0025] Example 3 was repeated, except that instead of sorbitol 20% by weight of glycerol was added.

Claims

1. A biodegradable, *i.e.* degradable in the environment, chewing gum comprising one or more conventional chewing gum components and as gum base at least one biodegradable polymer selected from the group of polyesters and polycarbonates, which polymer has a glass transition temperature of at most 37 °C, and which polymer contains in the polymer chain chemically unstable compounds which can be broken under the influence of light and/or hydrolytically.
2. , A chewing gum according to claim 1, wherein said polymer is a polyester, based on one or more cyclic esters, such as lactide, glycolide, TMC and epsilon-caprolactone.

3. A chewing gum according to claim 2, wherein the polyester is a copolymer of lactide and epsilon-caprolactone.
4. A chewing gum according to claims 2 or 3, wherein the polyester is a block copolymer of lactide and epsilon-caprolactone, or a mixture of a polymer of lactide and a polymer of epsilon-caprolactone.
5. A chewing gum according to any of the previous claims, wherein as additives one or more components are present, selected from the group consisting of fillers, antioxidants, plasticizers, sweeteners, flavouring substances, colouring substances, medicinal components and mouth conditioners.
6. A chewing gum according to any of the previous claims, wherein the gum base is present in an amount of 5 to 95% by weight, while further 5-95% by weight additives are present.
7. A chewing gum according to any of the previous claims, wherein further medicinal and/or mouth conditioning components are present.
8. Use of at least one biodegradable polymer containing chemically unstable compounds in the polymer chain and having a glass transition temperature of at most 37 °C, which polymer is selected from the group of polyesters and polycarbonates, as gum base of chewing gum.

Patentansprüche

1. Bioabbaubares, d.h. in der Umwelt abbaubares Kaugummi, umfassend eine oder mehrere herkömmliche Kaugummikomponenten und als Gummibasis mindestens ein bioabbaubares Polymer, ausgewählt aus der Gruppe von Polyestern und Polycarbonaten, wobei das Polymer eine Glasübergangstemperatur von höchstens 37°C hat und wobei das Polymer in der Polymerkette chemisch instabile Verbindungen, die unter dem Einfluss von Licht und/oder hydrolytisch aufbrechen, enthält.
2. Kaugummi gemäss Anspruch 1, wobei das Polymer ein Polyester auf Basis von einem oder mehreren cyclischen Estern ist, wie Lactid, Glycolid, TMC und ε-Caprolacton.
3. Kaugummi gemäss Anspruch 2, wobei der Polyester ein Copolymer von Lactid und ε-Caprolacton ist.
4. Kaugummi gemäss Anspruch 2 oder 3, wobei der Polyester ein Blockcopolymer von Lactid und ε-Caprolacton ist oder eine Mischung eines Lactidpoly-

mers und eines ε-Caprolactonpolymers.

5. Kaugummi gemäss einem der vorhergehenden Ansprüche, wobei als Zusatzstoffe eine oder mehrere Komponenten anwesend sind, ausgewählt aus der Gruppe, bestehend aus Füllmitteln, Antioxidanzien, Weichmachern, Süssmitteln, aromatisierenden Substanzen, farbgebenden Substanzen, medizinischen Komponenten und Mundkonditionierern.
6. Kaugummi gemäss einem der vorhergehenden Ansprüche, wobei die Gummibasis in einer Menge von 5 bis 95 Gew.% vorhanden ist, während weitere Zusatzstoffe mit 5 bis 95 Gew.% anwesend sind.
7. Kaugummi gemäss einem der vorhergehenden Ansprüche, wobei weitere medizinische und/oder mundkonditionierende Komponenten anwesend sind.
8. Verwendung von mindestens einem bioabbaubaren Polymer, enthaltend chemisch instabile Verbindungen in der Polymerkette, und mit einer Glasübergangstemperatur von höchstens 37°C, dieses Polymer ist ausgewählt aus der Gruppe von Polyestern und Polycarbonaten als Gummibasis für Kaugummi.

Revendications

1. Gomme à mâcher biodégradable, c'est-à-dire dégradable dans l'environnement, comprenant un ou plusieurs composant(s) classique(s) de gomme à mâcher et, en tant que gomme base, au moins un polymère biodégradable sélectionné parmi le groupe des polyesters et des polycarbonates, lequel polymère a une température de transition vitreuse d'au plus 37 °C, et lequel polymère contient des composés chimiquement instables dans la chaîne polymère qui peuvent se briser sous l'influence de la lumière et/ou hydrolytiquement.
2. Gomme à mâcher selon la revendication 1, dans laquelle ledit polymère est un polyester, basé sur un ou plusieurs esters cycliques, comme le lactide, le glycolide, le TMC et la ε-caprolactone.
3. Gomme à mâcher selon la revendication 2, dans laquelle le polyester est un copolymère de lactide et d'ε-caprolactone.
4. Gomme à mâcher selon la revendication 2 ou 3, dans laquelle le polyester est un copolymère bloc de lactide et d'ε-caprolactone, ou un mélange d'un polymère de lactide et d'un polymère d'ε-caprolactone.

5. Gomme à mâcher selon l'une quelconque des revendications précédentes, dans laquelle un ou plusieurs composant(s) est (sont) présent(s), comme additif(s), et est(sont) sélectionné(s) parmi le groupe consistant en charges de remplissage, antioxydants, plastifiants, édulcorants, substances aromatisantes, substances colorantes, composants médicaux et agents de conditionnement buccal. 5
6. Gomme à mâcher selon l'une quelconque des revendications précédentes, dans laquelle la gomme base est présente dans une quantité comprise entre 5 et 95 % en poids, alors que d'autres 5 à 95 % en poids d'additifs sont présents. 10
7. Gomme à mâcher selon l'une quelconque des revendications précédentes, dans laquelle d'autres composants médicaux et/ou de conditionnement buccal sont présents. 15
8. Utilisation d'au moins un polymère biodégradable contenant des composés chimiquement instables dans la chaîne polymère, et ayant une température de transition vitreuse d'au plus 37 °C, lequel polymère est sélectionné parmi le groupe des polyesters et des polycarbonates, en tant que gomme base de gomme à mâcher. 20
- 25

30

35

40

45

50

55